


Technical Notice – Sorting

Detectability and sorting of the colorant solution AMPACET / REC-NIR-BLACK 1900302-EA at sorting centres

This technical notice is also applicable for colorant solutions AMPACET / REC-NIR-BLACK 1900297-EA, REC-NIR-BLACK 1900555-K and REC-NIR-BLACK 1900302-KA

APPLICATION DESCRIPTION	GENERAL INFORMATION		
	Applicant	AMPACET	
	Application date	2019	
	Reference of the colorant solution	REC-NIR-BLACK 1900302-EA	
	Max. limit for concentration of the colorant solution	2%	
	DESCRIPTION OF THE COLORANT SOLUTION		
	Colour	Black	
	Colorant solution suitable for:	Rigid HDPE packaging	
	PURPOSE OF THE APPLICATION		
	To test the detectability of the black colorant solution AMPACET / REC-NIR-BLACK 1900302-EA, which is provided by AMPACET and used to colour rigid HDPE packaging, at French sorting centres.		

This notice relates only to the detectability of the colorant solution and not the recyclability of the packaging as a whole.



TECHNICAL CONCLUSIONS

Given the evidence provided to COTREP, and in view of the results presented in the test reports from optical sorting (O.S.) equipment manufacturers, AMPACET's black colorant solution REC-NIR-BLACK 1900302-EA used to colour rigid HDPE packaging is detectable by optical sorting in conditions representative of the technology used in French household packaging waste sorting centres. Use of a proportion of less than or equal to 2% of this colorant solution in rigid HDPE packaging will enable it to be sorted and directed to the HDPE packaging recycling stream with a satisfactory level of performance.

Although COTREP is issuing a positive opinion regarding the detectability of AMPACET's black colorant solution REC-NIR-BLACK 1900302-EA, this opinion provides no indication of the recyclability of the packaging as a whole.

This notice is valid when the colorant solution:

- is used in the manufacture of rigid HDPE packaging;
- has a maximum proportion of 2%;
- is not used with production scrap, other colorant solutions or recycled materials potentially containing carbon black.

COTREP reserves the right to review its opinion if the company modifies the composition of the colorant solution.

FIND OUT MORE

The extension of sorting guidelines to all plastic packaging has led to the modernisation of sorting centres in France. In particular, centres are automating their processes and acquiring optical separators using near infrared technology.

This step in the sorting process is critical to separating plastic packaging. It enables packaging to be sorted by resin and colour.

At this step in the sorting process, undetectable packaging is rejected by sorting centres and sent for energy recovery.

Carbon black pigment, which is currently widely used for dark-coloured packaging, absorbs infrared light emitted by the optical sorting equipment and returns no signal. Consequently, the packaging is not detected and therefore not recycled.

AMPACET's black colorant solution REC-NIR-BLACK 1900302-EA used to colour rigid HDPE packaging offers an alternative to undetectable colorant solutions. The results of static and dynamic tests performed on the premises of two O.S. manufacturers (PELENC SA and TOMRA) according to the COTREP procedure were positive. Rigid HDPE packaging containing 2% of black colorant solution REC-NIR-BLACK 1900302-EA was directed to the HDPE stream with the same level of performance (quality, capture rate) as other HDPE household packaging waste.

The conclusions set out in this notice are based on a set of commitments undertaken by each of the parties indicated below.

AMPACET undertook to:

- use the sorting procedure provided by COTREP ("COTREP optical sorting test procedure for assessing the detectability of dark packaging at optical sorting stages" - version of January 2019¹);
- perform tests on the premises of two O.S. manufacturers representative of existing sorting facilities in France;
- submit test reports to COTREP for its analysis and opinion;
- offer a colorant solution that:
 - o meets the essential requirements of the Packaging and Packaging Waste Directive (94/62/EC).
 - o does not alter the density of the packaging: the density of packaging mainly consisting of PP or PE must be < 1 and > 1 for packaging mainly consisting of PET or PS.

The O.S. manufacturers made an undertaking to COTREP to:

- follow the procedure in its entirety;
- perform tests using technologies and machine settings representative of those used in current sorting centres and under normal operating conditions.

Paris, 27 November 2019

¹ Available from the COTREP website: <https://www.cotrep.fr/content/uploads/sites/3/2019/02/tri-p1-emballages-sombres-v01-2019.pdf>