


Technical Notice – Sorting

Detectability and sorting of ANL PACKAGING / PP Brun NIR detect packaging at sorting centres

APPLICATION DESCRIPTION	GENERAL INFORMATION		
	Applicant	ANL PACKAGING	
	Application date	2019	
	Brand - Item	PP Brun NIR detect	
	Market	Thermoformed packaging for various food and non-food sectors	
	DESCRIPTION OF PACKAGING		
	Form	Tray	
	Colour	Brown	
	Dimensions	195 x 111 x 32 mm	
	MATERIALS		
Body	PP, 8% brown colorant Details of the colorant used are confidential. The exact reference of the colorant was provided to COTREP to enable it to issue this notice.		
PURPOSE OF THE APPLICATION			
To test the detectability of ANL PACKAGING / PP Brun NIR detect packaging at French sorting centres			

This notice relates only to the detectability of the packaging and not its recyclability.



Sorting centre
Ability of packaging waste to be channelled to the regeneration plant



Regeneration
Ability of packaging waste to be converted into ready-to-use flakes or granulate



Use of recycled material
Ability of flakes or granulate to be converted into new products

TECHNICAL CONCLUSIONS

Given the evidence provided to COTREP, and in view of the results presented in the test reports from optical sorting (O.S.) equipment manufacturers, ANL PACKAGING's PP Brun NIR detect packaging is detectable by optical sorting in conditions representative of the technology used in French household packaging waste sorting centres. This packaging can therefore be sorted and directed to the PP packaging recycling stream with a satisfactory level of performance. Although COTREP is issuing a positive opinion regarding the detectability of ANL PACKAGING's PP Brun NIR detect packaging, this opinion provides no indication of its recyclability. Moreover, COTREP reserves the right to review its opinion if the company modifies the packaging composition, e.g. by:

- modifying the resin¹;
- using recycled materials/production scrap potentially containing carbon black;
- modifying the colorant solution and/or its proportions.

¹ The term "resin" is understood to mean the type of polymer used, i.e. "PP", "PET" or "HDPE". The notice remains valid if the supplier of the type of polymer tested changes.

FIND OUT MORE

The extension of sorting guidelines to all plastic packaging has led to the modernisation of sorting centres in France. In particular, centres are automating their processes and acquiring optical separators using near infrared technology.

This step in the sorting process is critical to separating plastic packaging. It enables packaging to be sorted by resin and colour.

At this step in the sorting process, undetectable packaging is rejected by sorting centres and sent for energy recovery.

Carbon black pigment, which is currently widely used for dark-coloured packaging, absorbs infrared light emitted by the optical sorting equipment and returns no signal. Consequently, the packaging is not detected and therefore not recycled.

ANL PACKAGING's packaging is a brown PP thermoformed tray using an alternative colorant solution to carbon black at a concentration of 8%. Details of the colorant used are confidential. The exact reference of the colorant was provided to COTREP to enable it to issue this notice. The results of static and dynamic tests performed on the premises of two O.S. manufacturers (PELLENC SA and TOMRA) according to the COTREP procedure were positive. The ANL PACKAGING brown PP trays were directed to the PP stream with the same level of performance (quality, capture rate) as other PP household packaging waste.

The conclusions set out in this notice are based on a set of commitments undertaken by each of the parties indicated below.

ANL PACKAGING undertook to:

- use the sorting procedure provided by COTREP ("COTREP optical sorting test procedure for assessing the detectability of dark packaging at optical sorting stages" - version of January 2019²);
- perform tests on the premises of two O.S. manufacturers representative of existing sorting facilities in France;
- submit test reports to COTREP for its analysis and opinion;
- use a colorant solution that:
 - o meets the essential requirements of the Packaging and Packaging Waste Directive (94/62/EC).
 - o does not alter the density of the packaging: the density of packaging mainly consisting of PP or PE must be < 1 and > 1 for packaging mainly consisting of PET or PS.

The O.S. manufacturers made an undertaking to COTREP to:

- follow the procedure in its entirety;
- perform tests using technologies and machine settings representative of those used in current sorting centres and under normal operating conditions.

Paris, 20 December 2019

² Available from the COTREP website: <https://www.cotrep.fr/content/uploads/sites/3/2019/02/tri-p1-emballages-sombres-v01-2019.pdf>