



Technical Notice – Sorting

Detectability and sorting of NEXT EMBALLAGE / Barquettes et calages PP noirs (trays and inserts) at sorting centres

APPLICATION DESCRIPTION	GENERAL INFORMATION		
	Applicant	NEXT EMBALLAGE	
	Application date	2020	
	Brand - Item	Barquettes et calages PP noirs (trays & inserts)	
	Market	Food Industry	
	DESCRIPTION OF PACKAGING		
	Form	Thermoformed trays	
	Colour	Black	
	Valid for	Trays and inserts of minimum thickness 600µm. (Tested packaging: COUR PP SNC – 600µm – 3%)	
	MATERIALS		
Body	PP, 3% black colorant Details of the colorant used are confidential. The exact reference of the colorant was provided to COTREP to enable it to issue this notice.		
PURPOSE OF THE APPLICATION			
To test the detectability of NEXT EMBALLAGE's trays and inserts at French sorting centres			

This notice relates to the detectability and sortability of the packaging and not its recyclability.



Sorting centre
Detectability: Ability of packaging to be recognised by optical sorting systems
Sortability: Ability of packaging to be channelled to the correct stream



Regeneration
 Ability of packaging waste to be converted into ready-to-use flakes or granulate



Use of recycled material
 Ability of flakes or granulate to be converted into new products

TECHNICAL CONCLUSIONS

Given the evidence provided to COTREP, and in view of the results presented in the test reports from optical sorting (O.S.) equipment manufacturers, NEXT EMBALLAGE's tested packaging COUR PP SNC – 600µm – 3% of 600µm thickness is detectable by optical sorting in conditions representative of the technology used in French household packaging waste sorting centres.

Consequently, all NEXT EMBALLAGE Black PP trays and inserts with a thickness > 600µm can therefore be detected and channelled as PP packaging with a satisfactory level of performance.

Although COTREP is issuing a positive opinion regarding the detectability and sorting of NEXT EMBALLAGE trays and inserts, this opinion provides no indication of its recyclability.

Moreover, COTREP reserves the right to review its opinion if the company modifies the packaging composition, e.g. by:

- modifying the resin¹;
- using recycled materials/production scrap potentially containing carbon black;
- modifying the colorant solution and/or its proportions.

¹ The term “resin” is understood to mean the type of polymer used, i.e. “PP”, “PET” or “HDPE”. The notice remains valid if the supplier of the type of polymer tested changes.

FIND OUT MORE

The extension of sorting guidelines to all plastic packaging has led to the modernisation of sorting centres in France. In particular, centres are automating their processes and acquiring optical separators using near infrared technology.

This step in the sorting process is critical to separating plastic packaging. It enables packaging to be sorted by resin and colour.

At this step in the sorting process, undetectable packaging is rejected by sorting centres and sent for energy recovery.

Carbon black pigment, which is currently widely used for dark-coloured packaging, absorbs infrared light emitted by the optical sorting equipment and returns no signal. Consequently, the packaging is not detected and therefore neither sorted nor recycled.

NEXT EMBALLAGE's packaging comprises a range of black PP trays and inserts using an alternative colorant solution to carbon black at a concentration of 3%. Details of the colorant used are confidential. The exact reference of the colorant was provided to COTREP to enable it to issue this notice. The results of static and dynamic tests performed on the premises of two O.S. manufacturers (PELENC SA and TOMRA) according to the COTREP procedure were positive. The NEXT EMBALLAGE PP trays and inserts were detected as PP packaging with the same level of performance (quality, capture rate) as other rigid PP household packaging waste.

The conclusions set out in this notice are based on a set of commitments undertaken by each of the parties indicated below.

NEXT EMBALLAGE undertook to:

- use the sorting procedure provided by COTREP ("COTREP optical sorting test procedure for assessing the detectability of dark packaging at optical sorting stages" - version of January 2019²);
- perform tests on the premises of two O.S. manufacturers representative of existing sorting facilities in France;
- submit test reports to COTREP for its analysis and opinion;
- use a colorant solution that:
 - o meets the essential requirements of the Packaging and Packaging Waste Directive (94/62/EC).
 - o does not alter the density of the packaging: the density of packaging mainly consisting of PP or PE must be < 1 and > 1 for packaging mainly consisting of PET or PS.

The O.S. manufacturers made an undertaking to COTREP to:

- follow the procedure in its entirety;
- perform tests using technologies and machine settings representative of those used in current sorting centres and under normal operating conditions.

Paris, 19 March 2020 / Revised on 23 July 2020

² Available from the COTREP website: <https://www.cotrep.fr/content/uploads/sites/3/2019/02/tri-p1-emballages-sombres-v01-2019.pdf>