



## Technical Notice – Sorting

### Detectability and sorting of the colorant solution AVIENT CORPORATION / CESA® IR PE 94000828 at sorting centres

APPLICATION DESCRIPTION	<b>GENERAL INFORMATION</b>		
	Applicant	Avient Corporation	
	Application date	2020	
	Reference of the colorant solution	CESA® IR PE 94000828	
	Max. limit for concentration of the colorant solution	4%	
	<b>DESCRIPTION OF THE COLORANT SOLUTION</b>		
	Colour	Black	
	Colorant solution suitable for:	Rigid PE packaging	
	<b>PURPOSE OF THE APPLICATION</b>		
	To test the detectability of the colorant solution CESA® IR PE 94000828, which is provided by Avient Corporation and used to colour rigid PE packaging, at French sorting centres.		

**This notice relates to the detectability and sortability of the colorant solution and not the recyclability of the packaging as a whole.**



## TECHNICAL CONCLUSIONS

Given the evidence provided to COTREP, and in view of the results presented in the test reports from optical sorting (O.S.) equipment manufacturers, Avient Corporation's black colorant solution CESA® IR PE 94000828 used to colour rigid PE packaging is detectable by optical sorting in conditions representative of the technology used in French household packaging waste sorting centres. Use of a proportion of less than or equal to 4% of this colorant solution in rigid PE packaging will enable it to be detected and channelled to the PE packaging stream with a satisfactory level of performance.

Although COTREP is issuing a positive opinion regarding the detectability and sortability of Avient Corporation's black colorant solution CESA® IR PE 94000828, this opinion provides no indication of the recyclability of the packaging as a whole.

This notice is valid when the colorant solution:

- is used in the manufacture of rigid PE packaging;
- has a maximum proportion of 4%;
- is not used with production scrap, other colorant solutions or recycled materials potentially containing carbon black.

COTREP reserves the right to review its opinion if the company modifies the composition of the colorant solution.

## FIND OUT MORE

---

The extension of sorting guidelines to all plastic packaging has led to the modernisation of sorting centres in France. In particular, centres are automating their processes and acquiring optical separators using near infrared technology.

This step in the sorting process is critical to separating plastic packaging. It enables packaging to be sorted by resin and colour.

At this step in the sorting process, undetectable packaging is rejected by sorting centres and sent for energy recovery.

Carbon black pigment, which is currently widely used for dark-coloured packaging, absorbs infrared light emitted by the optical sorting equipment and returns no signal. Consequently, the packaging is not detected and therefore neither sorted nor recycled.

Avient Corporation's black colorant solution IR PE 94000828 used to colour rigid PE packaging offers an alternative to undetectable colorant solutions. The results of static and dynamic tests performed on the premises of two O.S. manufacturers (PELENC SA and TOMRA) according to the COTREP procedure were positive. Rigid PE packaging containing 4% of black colorant solution CESA® IR PE 94000828 was detected and channelled to the PE stream with the same level of performance (quality, capture rate) as other rigid PE household packaging waste.

The conclusions set out in this notice are based on a set of commitments undertaken by each of the parties indicated below.

Avient Corporation undertook to:

- use the sorting procedure provided by COTREP ("COTREP optical sorting test procedure for assessing the detectability of dark packaging at optical sorting stages" - version of January 2019<sup>1</sup>);
- perform tests on the premises of two O.S. manufacturers representative of existing sorting facilities in France;
- submit test reports to COTREP for its analysis and opinion;
- offer a colorant solution that:
  - o meets the essential requirements of the Packaging and Packaging Waste Directive (94/62/EC).
  - o does not alter the density of the packaging: the density of packaging mainly consisting of PP or PE must be < 1 and > 1 for packaging mainly consisting of PET or PS.

The O.S. manufacturers made an undertaking to COTREP to:

- follow the procedure in its entirety;
- perform tests using technologies and machine settings representative of those used in current sorting centres and under normal operating conditions.

Paris, 17 July 2020

---

<sup>1</sup> Available from the COTREP website: <https://www.cotrep.fr/content/uploads/sites/3/2019/02/tri-p1-emballages-sombres-v01-2019.pdf>